

Revision Date: 09.15.23



DEL-VAL 503 RC 400 TACK COAT

DESCRIPTION

Del-Val 503 RC 400 Tack Coat is an asphalt based cut-back product used for priming and bonding of asphalt surfaces. Del-Val 503 RC 400 Tack Coat is formulated with refined asphalts and is cut with 105°F flash point mineral spirits to a smooth consistency.

USES

Del-Val 503 RC 400 Tack Coat can be used as a prime coat on asphalt surfaces before overlaying new asphalt surfaces.

APPLICATION

Apply with a brush or spray equipment on a dry and clean surface. Surface must be dry and clean before applying.

COVERAGE


Approximately 150 sq. ft. per gallon.

PRECAUTION

DO NOT HEAT MATERIAL. **DANGER:** COMBUSTIBLE MIXTURE. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. HARMFUL OR FATAL IF SWALLOWED.



TOOLS NEEDED ▾



PACKAGING SIZES ▾



LEARN MORE ⬇

UnitedAsphalt.com/DV503

PHYSICAL PROPERTIES

| | |
|-----------------|------------------------|
| Color | Dark Brown-Black |
| Total Solids | 78% to 83% wt |
| Solvent Content | 17% to 22% wt |
| Solvent Type | Mineral Spirits |
| Flash Point | 105° F |
| Viscosity | 800 -1600 cSt @ 140° F |
| Wt/Gal | 8.1 lbs |

BASE ASPHALT

| | |
|-----------------|---------------|
| Softening Point | 115° - 130° F |
| Penetration | 60 - 110 |

CODE APPROVALS/COMPLIANCE

Meets: ASTM D-2028 and ASSHTO M81 Specifications

SCAN HERE ⬇



DEPEND ON
Del-Val
DELIVERING VALUE