

Revision Date: 03.01.23

Del-Val

DELIVERING VALUE

DEL-VAL 315 THERMOPLASTIC ROOF COATING

DESCRIPTION

Del-Val 315 Thermoplastic Roof Coating is a single-component, thermoplastic rubber coating formulated for protecting metal, wood, EPDM, APP, TPO and Hypalon. Del-Val 315 provides a waterproof, durable, seamless flexible weather resistant membrane with excellent elongation, tensile strength and UV protection.

PREPARATION

Surface must be pressure washed clean, free of all loose particles, dirt debris and other contaminants that could inhibit adhesion. Wire brushing may be recommended in addition to pressure washing the surface. The surface must be completely dry to prevent blistering of the product. Contact United Asphalt for more information.

COVERAGE AND DRYING TIMES

Apply Del-Val 315 by brush, 3/8" nap roller or airless sprayer, at a rate of 100 square feet per gallon, according to the substrate and condition. Two coats are recommended. Backrolling may be necessary to prevent pinholes. A minimum of 16 mils DFT is recommended to achieve optimal performance of the coating. Dry time is 2-6 hours. Cure time is 24-48 hours.

CLEANUP

Remove product from tools, etc., with Del-Val Orange Cleaner & Degreaser or mineral spirits, taking necessary precautions when handling combustible liquids. Clean hands with a waterless hand cleaner.


LIMITATIONS AND PRECAUTIONS

Do not apply when temperature is below 40° F during application or drying time. Apply product when relative humidity is below 90° F. Allow for adequate dry times between coats and inclement weather. Higher humidity or lower temperatures will slow down dry times.

LEARN MORE  [UnitedAsphalt.com/DV315](https://www.unitedasphalt.com/DV315)



TOOLS NEEDED



PACKAGING SIZES



CERTIFICATIONS

