

Revision Date: 03.01.23

Del-Val

DELIVERING VALUE

DEL-VAL 411 FIBERED FOUNDATION EMULSION

DESCRIPTION

Del-Val 411 Fibered Foundation Emulsion is manufactured from refined asphalts, reinforcing non-asbestos fibers and clays. Del-Val 411 Fibered Foundation Emulsion has a brown appearance when wet but will dry to a near black color. Asphalt emulsions are very low odor alternatives to solvent borne asphalt roof coatings. Del-Val 410 is applied directly from the container is corrosion-resistant, and waterproof when dry. Del-Val 410 does not crack, run or sag under extreme weather conditions. Del-Val 410 is a coating suitable for the protection of roofing materials, metal, and masonry surfaces. Del-Val 410 is reinforced with short fibers for application by brush, roller or spray.

USES

Del-Val 411 Fibered Foundation Emulsion is ideal for reducing dampness and moisture infiltration through foundation walls, parapets, firewalls, tanks, culverts, cisterns, and bridge abutments. Del-Val 410 is applicable for above-grade cavity wall applications and below-grade masonry wall damp proofing and helps to minimize internal structural damage from mildew and mold. Suitable for "green" or slightly damp surfaces.

APPLICATION

Apply with a four-knot brush, roller, or suitable spray equipment. Cover the surface at the rate of 3 gallons per 100 square feet per application. For added protection, apply a 2nd coat at the same rate as soon as the first coat is thoroughly dry. Apply the second coat at right angles to the first. Drying will be slower, 2 to 7 days, in cool, damp weather conditions. Allow Del-Val 410 to dry completely between coats. Coating becomes waterproof only after drying thoroughly.

For damp-proofing of below-grade exterior surfaces: When coating dense concrete surfaces not subject to hydrostatic pressure, a single coat of Del-Val 410 is generally adequate when applied at approximately 1/16" in thickness. If conditions are severe or when applying by spray, two coats of Del-Val 410 are preferable. Apply each coat at 3 gallons per 100 square feet, allowing first coat to dry before applying second coat. Fill in all crevices and grooves during application, making sure material is free from breaks and pinholes. Carry coating over exposed top and outside edge of footing.


Del-Val 411 Fibered Foundation Emulsion Coating may only be applied when temperatures are expected to remain above 50°F, and if no rain is expected, for the next 24 hours. Del-Val 410 dries in 8 to 12 hours in warm, dry weather. Drying can take from 2 to 7 days in cold, damp weather. Allow to dry between coats.

COVERAGE


Approximately 70 - 100 ft.²/gal. (1.71- 2.45 m²/L) per coat.



TOOLS NEEDED ▾



PACKAGING SIZES ▾



PRECAUTION

KEEP FROM FREEZING.
Do not take internally. Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. If swallowed, do not induce vomiting. KEEP OUT OF REACH OF CHILDREN.

LEARN MORE ↓

UnitedAsphalt.com/DV411