

DEL-VAL 504 RC 800 TACK COAT

DESCRIPTION

Del-Val 504 RC 800 Tack Coat is an asphalt based cut-back product used for priming and bonding of asphalt surfaces. Del-Val 504 RC 800 Tack Coat is formulated with refined asphalts and is cut with 105°F flash point mineral spirits to a smooth consistency.

USES

Del-Val 504 RC 800 Tack Coat can be used as a prime coat on asphalt surfaces before overlaying new asphalt surfaces.

APPLICATION

Apply with a brush or spray equipment on a dry and clean surface. Surface must be dry and clean before applying.

COVERAGE

Approximately 150 sq. ft. per gallon.

PRECAUTION

DO NOT HEAT MATERIAL. DANGER: COMBUSTIBLE MIXTURE. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. HARMFUL OR FATAL IF SWALLOWED.

PHYSICAL PROPERTIES	
Color	Dark Brown-Black
Total Solids	78% to 83% wt
Solvent Content	17% to 22% wt
Solvent Type	Mineral Spirits
Flash Point	105° F
Viscosity	800 -1600 cSt @ 140° F
Wt/Gal	8.1 lbs
BASE ASPHALT	
Softening Point	115° - 130° F
Penetration	60 - 110

CODE APPROVALS/COMPLIANCE

Meets: ASTM D-2028 and ASSHTO M81 Specifications



TOOLS NEEDED ~





PACKAGING SIZES ~



